







Naps Systems' 30 years of solar power experience in all continents and conditions provide the highest level of quality and power in an attractive and dependable package.

High power and efficiency

Naps Saana series of solar modules contain 60 high efficiency dark blue polycrystalline solar cells. The cells are carefully selected to assure a narrow and positive power range, thus minimising mismatch losses in the system.

The deeply textured surface of the prism glass improves light transmission to the solar cells. An increase of up to 3% is attained in the rated maximum power under Standard Test Conditions. At low sun elevation, the transmitted light is increased by up to 20%. In a typical grid-connected system in Germany and similar locations, the annual energy production is increased by approximately 5% compared to smooth glass modules of the same power rating.

Dependable construction and long life

Featuring the highest standards of construction and materials, Naps Saana solar modules are able to withstand the harshest environments and continue to perform efficiently. Properly installed, these modules have a design life well beyond the power warranty. Limited power warranties are given for both 10 and 25 years. The modules are tested to meet or exceed all relevant international standards and the highest requirements for quality and performance.



www.napssystems.com

Naps Saana 225-235G PB

Glass type:

Frame colour:

Backsheet colour:

PRISM

BLACK


WHITE

- Carefully selected polycrystalline silicon solar cells for close tolerance
- Solar cells treated for reduced reflection and for efficient conversion of both direct and diffuse light
- Electrical circuit laminated between layers of ethylene vinyl acetate (EVA) for electrical isolation, moisture resistance and **UV** stability
- Low iron content, tempered glass for mechanical protection and high light transmission
- The textured surface of the prism glass improves standard rated power by up to 3% and increases the current by up to 20% at low sun elevation
- · Multi-layered polymer backsheet for resistance to abrasion, tears and punctures and dependable electrical insulation
- Rugged and lightweight anodised aluminium frame with mounting, grounding and drainage holes
- Junction box with pre-fitted cables and quick connectors designed for ease and safety
- Wired-in bypass diodes to reduce potential loss of power and damage from partial array shading
- Tested for a wide range of operating conditions (-40°C to +85°C)
- Tested to withstand the highest wind, hail storm and snow load requirements (5400 N/m²)
- Designed to meet or exceed the environmental requirements of IEC61215
- Designed to meet the requirements of IEC61730, including Safety Class II to IEC61140




Specifications: Naps Saana 225-235G PBW


| Performance at STC | 225G PBW | 230G PBW | 235G PBW |
|--|----------|----------|----------|
| Product code | 13225 | 13230 | 13235 |
| Maximum power (W/Pmax) | 225 | 230 | 235 |
| Maximum power tolerance (W) | +5/-0 | +5/-0 | +5/-0 |
| Current (typical at max power) (A/Ip) | 7.80 | 7.97 | 8.13 |
| Voltage (typical at max power) (V/Vp) | 28.9 | 28.9 | 28.9 |
| Short circuit current (typical) (A/Isc) | 8.44 | 8.59 | 8.74 |
| Open circuit voltage (typical) (V/Voc) | 36.9 | 37.0 | 37.1 |
| Module efficiency (minimum) (%) | 14.1 | 14.4 | 14.7 |
| Module efficiency (maximum) (%) | 14.4 | 14.7 | 15.0 |
| Performance at NOCT and 800 W/m ² | 225G PBW | 230G PBW | 235G PBW |
| Maximum power (W/Pmax) | 161.8 | 165.5 | 169.2 |
| Current (typical at max power) (A/Ip) | 6.19 | 6.33 | 6.47 |
| Voltage (typical at max power) (V/Vp) | 26.1 | 26.1 | 26.2 |
| Short circuit current (typical) (A/Isc) | 6.83 | 6.95 | 7.07 |
| Open circuit voltage (typical) (V/Voc) | 33.8 | 33.9 | 33.9 |




Module Dimensions



Voltage / Current Dependence on Temperature



Voltage / Current Dependence on Irradiance













| | | Joial Cells |
|------|--|--------------------------------|
| - 1 | | |
| | Mechanical Details | |
| | Overall length (mm) | |
| | Overall width (mm) | 986 |
| | Area (m²) | 1.601 |
| | Thickness at edge (mm) | 35 |
| | Weight (kg) | 21.6 |
| | Construction | |
| - | Cell type | polycrystalline |
| | Cells | 60 |
| | Cell dimensions (mm) | 156 x 156 |
| | Cell electrical circuit (series x parallel) | 60 x 1 |
| | Cell layout (horizontal x vertical) | 6 x 10 |
| | Glass thickness (mm) | 4.0 |
| | Junction box type | S PV1410-2 |
| b to | Bypass diodes factory fitted | |
| Т | Cables (4.0 mm²) | 2 x 1 m |
| | Connector type | x push-pull 4mm |
| | Other connector options available to special | order |
| | Protection Class | |
| | IEC61730 Application Class A, equivalent to | Safety Class II |
| | Maximum System Voltage | |
| | Voltage (V) | 1000 |
| | | 1000 |
| | Overcurrent Protection Series fuse protection rating (A) | 10 |
| | Series tuse protection rating (A) | 15 |
| | Reverse current maximum (A) | 15 |
| | Mechanical Load | |
| | Tested to (N/m² = Pa) | 5400 |
| | According to IEC 61215-2 extended test for | heavy snow load |
| | Temperature Coefficients at STC typ | e |
| 50. | Open circuit voltage (V/K) | 0.133 |
| | Short circuit current (A/K) | 0.0039 |
| 95, | Maximum power (%/K) | |
| | Efficiency Reduction from STC | |
| | Reduction (approximately) (%) | 5 |
| | Cell temperature (°C) | 25 |
| | Irradiance change (W/m²)f | rom 1000 to 200 |
| | Air Mass | |
| 88 | STC = Standard Test Conditions | |
| | Cell temperature (CC) | Ar. |
| | Cell temperature (°C) | 1000 |
| | Air Mass | 1 5 |
| | | |
| | NOCT = Normal Operating Cell Temp | erature |
| | Cell temperature (°C) | 46 |
| | Irradiation (W/m²) | 800 |
| | Ambient temperature (°C) | |
| - | Wind speed (m/s) | 1 |
| | Free air access to module rear | |
| | ATT AND A STATE OF THE PARTY. | A COLUMN TWO IS NOT THE OWNER. |
| | The second secon | |

